

**UNCLASSIFIED**

**AD** **409 316**

**DEFENSE DOCUMENTATION CENTER**

**FOR**

**SCIENTIFIC AND TECHNICAL INFORMATION**

**CAMERON STATION, ALEXANDRIA, VIRGINIA**



**UNCLASSIFIED**

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

CATALOGED BY DDC 316  
AS AD No. \_\_\_\_\_

1 AFCRL-63-120(B)

409 316

63-4-2

SEMICONDUCTOR DEVICE CONCEPTS

General Electric Company  
Advanced Semiconductor Laboratory  
Syracuse, New York

Scientific Report No. 3B

AF 19(628)-329


Project 4608

Task 460804

February 28, 1963

Prepared for

AIR FORCE CAMBRIDGE RESEARCH LABORATORIES  
OFFICE OF AEROSPACE RESEARCH  
UNITED STATES AIR FORCE  
BEDFORD, MASSACHUSETTS



Requests for additional copies by Agencies of the Department of Defense, their contractors, and other Government agencies should be directed to the:

DEFENSE DOCUMENTATION CENTER (DDC)  
ARLINGTON HALL STATION  
ARLINGTON 12, VIRGINIA

Department of Defense contractors must be established for ASTIA services or have their "need-to-know" certified by the cognizant military agency of their project or contract.

All other persons and organizations should apply to the:

U. S. DEPARTMENT OF COMMERCE  
OFFICE OF TECHNICAL SERVICES  
WASHINGTON 25, D. C.

## Table of Contents

Abstract .....	iii
Introduction .....	1
A. Preparation of $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ Crystals and Laser p-n Junctions .....	2
B. Electrical and Optical Properties of $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ Laser Junctions .....	5
References .....	11
Figure Captions .....	12

### Abstract

A status report on the preparation and properties of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  p-n junction lasers is presented. Halogen vapor transport synthesis of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  and its preparation into laser junctions are described. Electrical and optical properties of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  laser junctions are discussed. The present limitations in these properties are related to material problems and the very early state of development of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ , and are discussed in this context.

## Introduction

In this report we wish to describe briefly some of the salient features of now approximately five or more months experience with the preparation and properties of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  p-n junction lasers. Because much data so far available are incomplete, some of the results at this point must be considered tentative and subject to revision as work on  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  progresses.

Although the electrical, optical, and device properties of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  junction lasers are understandably of great interest, the work to date points out that by far currently the greatest problems and those deserving first attention are those involving the growth, doping, and perfection of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  crystals. Hence, even though the laser junctions prepared in this material are of importance in their own right, we have considered them at this point mainly as a means to study  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ . It can be concluded that the laser junctions now available are very much limited by the deficiencies of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  crystals and can not be fairly compared with GaAs p-n junction lasers until  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  crystal growth has been more extensively developed. The basis for these statements will become evident in the following sections which describe  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  crystal and junction preparation and junction properties.

#### A. Preparation of $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ Crystals and Laser p-n Junctions

As previously mentioned<sup>1</sup>, we have found it convenient to employ the halogen vapor transport process<sup>2</sup> for synthesizing  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  crystals for use in laser junctions. In the present work commercially available GaAs and GaP separately prepared by halogen vapor transport<sup>2</sup> are sealed in a quartz vessel with a quantity of column VI donor and a small quantity of metal halide which supplies the halogen for transport. The sealed ampoule is heated at a temperature in the range from 1000°C to 1100°C at the position of the source GaAs and GaP. The GaAs and GaP is simultaneously vapor transported and deposited as  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  at one end of the ampoule held at a lower temperature (between 900°C and 1050°C).

With this process we have been able to grow some large single crystal sections and a number of polycrystalline ingots of large crystallite diameters, which have been further processed into laser junctions by methods more or less similar to those employed with GaAs. Of the crystals so prepared a small quantity has yielded material of "laser quality".  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  prepared from commercially available GaP thus far has failed to yield laser junctions, perhaps because of carbon contamination. In a number of cases "good quality"  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  which has provided strong incoherent junction luminescent light sources has failed to "lase" because of insufficient donor doping in the crystal. The crystals which have "lased" have been doped to  $\sim 10^{18}$  donors/cm<sup>3</sup> and have been freer of strain than "non-lasing" crystals<sup>3</sup>. Also, the crystals that "lase" have tended to be freer of various dark spots which are evident under IR examination<sup>3</sup>.

The fact that preparation of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  of adequate quality poses the greatest obstacle to preparation of laser junctions is evident from a cursory examination of the journal literature. Lasers in  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  were reported<sup>1</sup> only slightly after the first



reported GaAs junction lasers of Hall, et al<sup>4</sup>, and well before most subsequent confirming reports of laser action in GaAs. Nevertheless, recent reports and, in fact, the journal literature for a period well beyond five months of Hall's, et al<sup>4</sup> first report of GaAs junction lasers contain hardly any mention of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ , almost as though (contrary to fact)  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  will not "lase". This queer circumstance, in spite of the great interest, flexibility, and importance of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ , is due simply to the lack of laser quality  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  and the difficulty in its synthesis to requisite perfection, purity, and doping.

Following synthesis of "suitable"  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  crystals the procedures we have used for fabrication of laser junctions follow closely those employed with GaAs. Suitably cut wafers are polished and are zinc diffused in sealed ampoules at temperatures as high as  $1000^\circ\text{C}$ . Long strips are cut out of the wafers, polished on the cut sides at right angles to the junction plane, and are separated into small sections to which electrical connections can be easily alloyed. (Or, when desired, p+ zinc-doped  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  layers have been epitaxially grown by the vapor transport process<sup>2</sup> on n-type wafers to form p-n junctions.)

From the crystals grown to date of the order of 100 laser p-n junctions have been assembled. It is interesting to note that since these laser junctions have operated at a number of wavelengths, almost all different,  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  has perhaps already "lased" at as many different wavelengths as all other solid state lasers combined. This could be expected<sup>1</sup>, for as shown by Fig. 1, reproduced from Ehrenreich's work<sup>5</sup> and changed to correspond to  $77^\circ\text{K}$ ,  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  is expected to be direct over a composition range from 0 % to 50 % phosphorus ( $0 \leq x \leq 0.5$ ) and a corresponding wavelength range from  $\sim 8400\text{\AA}$  to  $\sim 6000\text{\AA}$  (or less,  $77^\circ\text{K}$ ).

It should be mentioned that our experimental data and points when inserted upon Fig. 1 tend to fall below the theoretical curve

and indicate an energy gap less than predicted. This may imply that heavy donor or acceptor doping in our junctions smears the band edges and narrows the energy gap. This would imply further that it may be difficult or impossible to achieve laser wavelengths near  $6000\text{\AA}$  in  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$ . Also, if this interpretation is correct, it may be equally difficult or impossible to establish that discrete donor or acceptor levels are involved in the light producing recombination process. In fact, in contradiction to several schools of thought believing donor or acceptor levels are involved in the recombination luminescence process in GaAs, we see no evidence in  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  to favor this belief at this time.

## B. Electrical and Optical Properties of Ga(As<sub>1-x</sub>P<sub>x</sub>) Laser Junctions

In an earlier report<sup>6</sup> we described the high quality I-V characteristics and sharp avalanches which can be obtained in Ga(As<sub>1-x</sub>P<sub>x</sub>) p-n junctions. Recent investigations have shown that in several respects the avalanche properties of Ga(As<sub>1-x</sub>P<sub>x</sub>) may excel silicon<sup>7</sup>. On units of comparable area lower noise and lower dynamic impedance have been observed in Ga(As<sub>1-x</sub>P<sub>x</sub>).

Aside from various inhomogeneities in Ga(As<sub>1-x</sub>P<sub>x</sub>), currently one of the more serious problems is that associated with contaminating impurities and resultant deep levels. The effects of deep levels on Ga(As<sub>1-x</sub>P<sub>x</sub>) p-n junctions are generally evident at low temperatures. Where such levels abound, just as in GaAs the forward I-V characteristic becomes higher impedance at lower temperatures, and may even exhibit negative resistance behavior. These are familiar double-injection effects<sup>8</sup> and are a direct consequence of deep levels. Unfortunately these effects compete with the high-efficiency, direct recombination process by allowing carrier recombination to occur in "steps" via deep levels. In the many instances that we have observed these effects, as expected, we have not been able to obtain stimulated emission. So far, we have not identified specific impurities which contribute deep levels but regard O<sub>2</sub> as a likely suspect since it is a major constituent of our synthesis vessel and since a number of the elements present in the synthesis process may react with the quartz synthesis vessel. At any rate, the observation of deep level effects in Ga(As<sub>1-x</sub>P<sub>x</sub>) junctions underscores the need to continue improving synthesis and growth techniques and crystal quality.

An interesting and important question concerning laser junctions is that of the mechanism of light generation and the

related question of where in the junction region the recombination process (and radiation) occur. To study this problem we have examined  $\sim 10$  laser junctions which have been cross-sectioned and polished normal to the junction plane. With a mild etch slight "moats" were cut into the polished sections in order to reveal the junction transition regions. In order to remove errors of focusing inherent in dispersion effects at different wavelengths, we examined the junction cross-sections at high power under incident red light and with the sectioned but operative junctions supplying recombination radiation (red).

In each case in which the experiment was carefully performed the source of recombination radiation (red) and junction "moat" coincided, with no indication that either n-side or p-side of the junction transition supplied more light. Assuming that the etched moat truly coincides with the junction transition region, which is a reasonable first order assumption, we conclude (until better evidence is obtained) that the recombination process (and radiation) occurs right in the junction transition region. These results and the fact that these junctions are heavily doped on n- and p-type sides suggest that these devices are much like p-i-n structures of exceedingly narrow extent between n- and p-side (very narrow "i"-region, but not "tunneling" narrow or a true "step" transition). This conclusion is consistent with the earlier observation of the "snap-off" behavior of stored charge in  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  laser junctions<sup>6</sup>, again indicative of the fact that the injected positive and negative charge is in the form of a thin sheet probably residing right in the transition or thin "i" region.

It should be noted that the discussion above does not necessarily imply that discrete acceptor or donor levels are not involved in the recombination process. However, the evidence that

the recombination radiation originates in the junction transition region (rather than on either side) plus the likelihood that the high acceptor and donor concentrations smear both band edges through the transition region make uncertain the view that discrete levels play a primary role in the recombination process.

In an earlier publication<sup>9</sup> we showed that at the current threshold for laser action  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  junctions first exhibit laser action in discrete regions through the junction plane from one polished face to the other. As the driving current is increased these lasing regions increase in size or other separate regions begin to exhibit laser action, and not necessarily at the same or mode-related wavelength of the first region. From cross-sections of laser junctions we have found that some junctions do not lase uniformly throughout the junction plane because of pronounced localized dips or spikes in the junction plane. In fact, usually in  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  junctions polished on all four sides, i.e. polished on the four sides bounding and at right angles to the junction plane, laser action will generally occur anomalously along the short dimension of the junction plane rather than along the long dimension because of localized dips, spikes, and assorted flaws in the junction. Laser action occurs in the short dimension because light traveling from polished face to polished face in the junction plane is not as apt to find an interruption in geometry as in the long dimension. These observations further point up the need for an intensive effort to improve the quality of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  crystals.

The usual optical transmission procedures for examining the band gap of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  prepared by halogen vapor transport generally show that the composition of the material is close to that predicted on the basis of the known initial quantities of GaAs and GaP used in the synthesis process. Laser junctions, on the

contrary, show that even though  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  can have a well-defined band structure and a good microscopic composition, significant macroscopic fluctuation can occur in As:P ratio in the material. This is evident from the laser junction spectra shown in Fig. 2. The sharp transition from incoherent operation at 20A to laser operation at 22A is shown by curves a) and b), both taken with spectrometer and amplifier settings constant. Curve b) shows laser action at wavelengths separated by almost  $40\text{\AA}$  and an independently measured spatial separation of  $\sim 2 \times 10^{-2}$  cm between the two laser beams. The diode operates almost as though it were two different laser junctions, each with the same length cavity (Fabry-Perot structure) but with differing  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  composition and band gap. In laser junctions in which the As:P ratio is spatially more homogeneous across the junction plane the spectral output is confined to a much smaller band than the diode of Fig. 2. Also, where a number of spectral peaks are observed they occur as well-defined modes with uniform spacing. In one such case we have counted 30 uniformly spaced modes in a spectral band  $\sim 30\text{\AA}$  wide.

An indication of the efficacy of laser action in  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  p-n junctions is supplied by Fig. 3, which shows the spectral output of junction 95-1 with current excitation [a) 12A] just below threshold and [b) 13A] just above threshold (spectrometer, photomultiplier voltage, and amplifier settings all constant). Above threshold the spectral output narrows sharply, and for less than a 10 % change in current drive (excitation) the peak spectral output increases by more than 10x. Laser junctions of this type with less than 2 mW average input power produce enough coherent light (half the output coherent light) so that the diverging beam can be condensed, and focused and be easily observed on screens at distances beyond 60 feet. For the diodes we have examined the coherent light output falls in a cone of esti-

mated half-angle  $\sim 5^\circ$ . The coherent light output can be displayed easily on a screen or ground glass plate in a red-colored version of the familiar diffraction pattern first described by Hall, et al<sup>4</sup>.

## Contributors and Contract Activity

Scientists and technical staff who contributed to the work reported:

### Staff Members

N. Holonyak, Jr.  
C. V. Bielan

### Technical Staff

S. F. Bevacqua  
F. A. Carranti  
B. G. Hess  
S. J. Lubowski

Papers published under contract:

1. N. Holonyak, Jr. and S. F. Bevacqua, Appl. Phys. Letters 1, 82 (1962).
2. N. Holonyak, Jr., et al., Proc. Inst. Elec. Elec. Engrs. 51, 364 (1963).
3. N. Holonyak, Jr., Electronics 36, 35 (March 1, 1963).

Seminar presentations during contract:

N. Holonyak, Jr., Univ. of Illinois, Dec., 1962.  
N. Holonyak, Jr., Syracuse Univ., Jan., 1963.  
N. Holonyak, Jr., Syracuse Section I.E.E.E.-P.G.M.T.T.,  
Feb., 1963.



### References

1. N. Holonyak, Jr. and S. F. Bevacqua, Appl. Phys. Letters 1, 82 (1962).
2. N. Holonyak, Jr., D. C. Jillson, and S. F. Bevacqua, Chap. 15, pp. 49-59, Metallurgy of Semiconductor Materials 15 (Proceedings of A.I.M.E. Conf., Los Angeles, Aug. 30-Sept. 1, 1961; Interscience Div. of John Wiley, N.Y., N.Y., 1962).
3. We are grateful to R. N. Hall for IR and birefringence analysis of a number of our crystals and laser junctions.
4. R. N. Hall, G. E. Fenner, J. D. Kingsley, T. J. Soltys, and R. O. Carlson, Phys. Rev. Letters 9, 366 (1962).
5. H. Ehrenreich, J. Appl. Phys. 32, 2155 (1961).
6. N. Holonyak, Jr., et al., Proc. Inst. Elec. Elec. Engrs. 51, 364 (1963).
7. F. Gentry, private communication.
8. N. Holonyak, Jr., Proc. Inst. Radio Engrs. 50, 2421 (1962).
9. N. Holonyak, Jr., Electronics 36, 35 (March 1, 1963).

### Figure Captions

- Fig. 1 Energy gap as a function of composition for  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  at  $77^\circ\text{K}$  (after Ehrenreich, J. Appl. Phys. 32, 2155, 1961).
- Fig. 2 Spectral output of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  diode 95-4 at  $77^\circ\text{K}$ .  
a) Below threshold (20A), b) above threshold (22A). At 22A output consists of two coherent light sources separated spatially by  $\sim 2 \times 10^{-2}$  cm and differing in wavelength by  $\sim 40\text{\AA}$ .
- Fig. 3 Spectral output of  $\text{Ga}(\text{As}_{1-x}\text{P}_x)$  diode 95-1 at  $77^\circ\text{K}$  when operated just below threshold a) and just above threshold b). Scale same for a) and b).




FIG. 1




FIG. 2




FIG. 3

DISTRIBUTION LIST - AF Contract No. AF19(628)-329

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
AF 5	AFMTC (AFMTC Tech Library - MU-135) Patrick AFB, Fla.	1
AF 18	AUL Maxwell AFB, Ala.	1
AF 32	OAR (RROS, Col. John R. Fowler) Tempo D 4th and Independence Ave. Washington 25, D. C.	1
AF 33	AFOSR, OAR (SYRP) Tempo D 4th and Independence Ave. Washington 25, D. C.	1
AF 43	ASD (ASAPRD - Dist) Wright-Patterson AFB, Ohio	1
AF 124	RADC (RAALD) Griffiss AFB, New York Attn: Documents Library	1
AF 139	AF Missile Development Center (MDGRT) Holloman AFB, New Mexico	1
AF 314	Hq. OAR (RROSP, Maj. Richard W. Nelson) Washington 25, D. C.	1
Ar 5	Commanding General USASRDL Ft. Monmouth, N. J. Attn: Tech. Doc. Ctr. SIGRA/SL-ADT	1
Ar 9	Department of the Army Office of the Chief Signal Officer Washington 25, D. C. Attn: SIGRD-4a-2	1
Ar 50	Commanding Officer Attn: ORDTL-012 Diamond Ordnance Fuze Laboratories Washington 25, D. C.	1

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
Ar 67	Redstone Scientific Information Center U. S. Army Missile Command Redstone Arsenal, Alabama	1
G 2	ASTIA (TIPAA) Arlington Hall Station Arlington 12, Virginia	20
G 31	Office of Scientific Intelligence Central Intelligence Agency 2430 E Street, N. W. Washington 25, D. C.	1
G 68	Scientific and Technical Information Facility Attn: NASA Representative (S-AK/DL) P. O. Box 5700 Bethesda, Maryland	1
G 109	Director Langley Research Center NASA Langley Field, Virginia	1
N 9	Chief, Bureau of Naval Weapons Department of the Navy Washington 25, D. C. Attn: DLI-31	2
N 29	Director (Code 2027) U. S. Naval Research Laboratory Washington 25, D. C.	2
I 292	Director, USAF Project RAND The Rand Corporation 1700 Main Street Santa Monica, California THRU: AF Liaison Office	1
M 6	AFCRL, OAR (GRXRA - Stop 39) L. G. Hanscom Field Bedford, Mass.	20
AF 253	Technical Information Office European Office, Aerospace Research Shell Building, 47 Cantersteen Brussels, Belgium	1

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
Ar 107	U. S. Army Aviation Human Research Unit U. S. Continental Army Command P. O. Box 428 Fort Rucker, Alabama Attn: Maj. Arne H. Eliasson	1
G 8	Library Boulder Laboratories National Bureau of Standards Boulder, Colorado	2
M 63	Institute of the Aerospace Sciences, Inc. 2 East 64th Street New York 21, New York Attn: Librarian	1
M 84	AFCRL, OAR (CRXR, J. R. Marple) L. G. Hanscom Field Bedford, Mass.	1
N 73	Office of Naval Research Branch Office, London Navy 100, Box 39 F.P.O., New York, N. Y.	10
U 32	Massachusetts Institute of Technology Research Laboratory Building 26, Room 327 Cambridge 39, Mass. Attn: John H. Hewitt	1
U 431	Alderman Library University of Virginia Charlottesville, Virginia	1
G 9	Defense Research Member Canadian Joint Staff 2450 Massachusetts Ave., N.W. Washington 8, D. C.	1
AF 318	Aero Research Lab (OAR) AROL Lib. AFL 2292, Bldg. 450 Wright-Patterson AFB, Ohio	1
	Watson Research Labs International Business Machines Corp. Yorktown Heights, New York Attn: Dr. A. Reisman	1



<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
Ar 62	Commanding Officer U.S. Army Signal R and D Laboratory Attn: SIGRA/SL-PRG (M. Zinn) Fort Monmouth, N. J.	1
I 44	Bell Telephone Laboratories, Inc. Murray Hill, N. J. Attn: Dr. J. Early	1
I 212	Philco Research Division Blue Bell, Pa. Attn: Dr. Richards	1
I 222	Clevite Corporation Electronic Research Division 540 East 105th Street Cleveland 8, Ohio Attn: P. L. DiRenzo, Project Administrator	1
I 886	Radio Corporation of America RCA Laboratories Princeton, N. J. Attn: Dr. A. G. Fischer	1
I 979	Radio Corporation of America • RCA Laboratories Princeton, N. J. Attn: Dr. William Webster	1
N 2	Chief, Bureau of Ships Department of the Navy Attn: Mr. A. H. Young, Code 681A1A Washington 25, D. C.	1
U 46	Mr. Donald O. Smith Lincoln Laboratory P. O. Box 73 Lexington 73, Mass.	1
U 269	Stanford Electronics Laboratories Stanford University Stanford, California Attn: Dr. J. G. Linville	1
U 274	The University of Wisconsin College of Engineering Madison 6, Wisconsin Attn: Alwyn Scott, Assistant Professor	1

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
I 821	Xerox Corporation Research and Engineering Center 800 Phillips Road Webster, New York Attn: Dr. F. A. Schwartz Director of Applied Research	1
I 272	Hoffman Electronics Corp. Hoffman Drive Santa Barbara, California Attn: David M. Heinz	1
AF 137	ASD (ASRNEM, Mr. Richard Alberts) Wright-Patterson AFB, Ohio	1
AF 138	ASD (ASRNEM-1, Mrs. E. Tarrants) Wright-Patterson AFB, Ohio	1
AF 251	ASD (ASRNOO) Wright-Patterson AFB, Ohio	2
Ar 56	U.S. Army Signal Supply Agency 225 South Eighteenth Street Philadelphia 3, Penna. Attn: G. I. Cooper Industrial Mobilization Agency	1
Ar 83	USASRDL Attn: SIGRA/SL-PD, H. Jacobs Fort Monmouth, N. J.	1
G 27	National Bureau of Standards U.S. Department of Commerce Attn: Mr. Gustave Shapiro, Chief Engineering Electronics Section Electricity and Electronics Division Washington 25, D. C.	1
G 64	Director National Security Agency Fort George G. Meade, Maryland Attn: REMP-2 Capt. A.M. Cole	1

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
G 70	Advisory Group on Electron Devices (AGED) 346 Broadway, 8th Floor Office of the Director of Defense Research and Engineering New York 13, N. Y.	4
G 78	Armed Services Electro Standards Agency Fort Monmouth, N. J. Attn: C. J. Held, AF Representative	1
G 80	National Bureau of Standards Department of Commerce Washington, D. C. Attn: Richard L. Raybold Electron Devices Section Electricity and Electronics Division	1
G 106	Director National Security Agency Fort Meade, Maryland Attn: R422-JTT	1
I 11	Motorola Semiconductors, Inc. 5005 E. McDowell Rd. Phoenix, Arizona Attn: Dr. Arnold Lesk	1
I 287	Philco Corporation Research Division Union Meeting Road Blue Bell, Pa. Attn: Research Librarian	1
I 503	Philco Corporation Research Division Union Meeting Road Blue Bell, Pa. Attn: Dr. A. J. Crocker	1
I 511	General Telephone and Electronics Laboratories, Inc. 208-20 Willets Point Boulevard Bayside, L. I., N. Y. Attn: T. Smith, Librarian	1
I 618	Motorola, Inc. Phoenix Research Lab. 3102 W. 56th St., Phoenix, Arizona Attn: C. L. Hogan, Semiconductor Prods. Div.	2

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
I 644	Central Research Laboratory Texas Instruments, Inc. 6000 Lemmon Avenue Dallas 9, Texas Attn: Dr. Gordon Teal	1
I 671	Texas Instruments, Inc. Semiconductor-Components Library P. O. Box 5012 Dallas 22, Texas	1
I 734	Sylvania Semiconductor Div. Sylvania Electronic Products, Inc. 100 Sylvan Road Woburn, Mass. R and E Librarian	1
I 735	Raytheon Corp. Seyon Street Waltham, Mass. Attn: Dr. Crawford Dunlap	1
I 738	Pacific Semiconductors, Inc. 10451 West Jefferson Blvd. Culver City, California Attn: Dr. Harper Q. North	1
I 740	Aerospace Corporation P. O. Box 95085 Los Angeles 45, Calif. Attn: Lee W. Aukerman Electronics Research Laboratory	1
I 749	Westinghouse Electric Corp. Pennsylvania Avenue Wilkesburg, Pa. Attn: Dr. Henry Chang	1
I 807	Shockley Transistor Corp. 391 S. Antonio Road Mountain View, Calif. Attn: A. Goetzberger	1
I 811	Hughes Aircraft Hughes Semiconductor Division Culver City, California Attn: Earl Steele	1

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
I 812	Fairchild Semiconductor Corp. 844 Charleston Rd. Palo Alto, Calif. Attn: Victor H. Grinich	1
I 820	Raytheon Company Research Division Waltham, Mass. Attn: Jerome M. Lavine	1
I 875	Merck, Sharp and Dohme Research Laboratories Rahway, New Jersey Attn: Mr. Gerald Conrad Physical and Inorganic Chemical Research	1
I 876	Bell Telephone Laboratories, Inc. Murray Hill, N. J. Attn: Mr. J. M. Whelan - 1132	3
I 903	Merck, Sharp and Dohme Research Labs Rahway, New Jersey Attn: Peter I. Pollak	1
I 904	General Telephone and Electronics Labs. Bayside, Long Island, N. Y. Attn: Mr. Sumner Mayburg	1
I 905	IBM Research Center P. O. Box 390 Poughkeepsie, New York Attn: Mr. M. K. Weiser	1
I 907	Raytheon Company Semiconductor Division 150 California Street Newton 58, Mass. Attn: Library	1
I 920	RCA Corporation Semiconductor and Materials Div. Route 202 Somerville, New Jersey Attn: R. Glicksman, Dept. 611	1
I 951	Westinghouse Electric Corp. Materials Laboratories, Solid State Elec. Dept. 7325 Penn Ave. Pittsburgh 8, Penna. Attn: J. Oroshnik, S.S.E.D.	1

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
I 953	Haloid Xerox, Inc. Rochester 3, New York Attn: E. M. Pell, Manager Solid State Research Dept.	1
I 980	Bell Telephone Laboratories Murray Hill, N. J. Attn: Mr. J. K. Galt	2
I 992	Services Electronics Research Laboratory Baldock, England Attn: Dr. C. Hilsum	1
I 1000	The Harshaw Chemical Company Attn: Dr. A. E. Middleton 1945 East 97th Street Cleveland 6, Ohio	1
M 50	AFCRL, Office of Aerospace Research (CRV) L. G. Hanscom Field Attn: Mr. C. E. Ryan Bedford, Mass.	2
M 51	AFCRL, Office of Aerospace Research (CRVPD, Dr. A. Yang) L. G. Hanscom Field Bedford, Mass.	5
M 52	AFCRL, Office of Aerospace Research (CRV), Dr. Bernard Rubin L. G. Hanscom Field Bedford, Mass.	1
M 60	ESD (ESRDE) Maj. James Van Horn L. G. Hanscom Field Bedford, Mass.	1
M 75	AFCRL, Office of Aerospace Research (CRVPD) Mr. R. F. Cornelissen L. G. Hanscom Field Bedford, Mass.	5
N 23	Commander U. S. Naval Ordnance Laboratory White Oak, Silver Spring 19, Md. Attn: The Library, HL-2	1

<u>Code</u>	<u>Organization</u>	<u>No. of Copies</u>
N 79	Chief, Bureau of Ships Department of the Navy Tubes and Semiconductors Unit Code 691A, Mr. R. A. Hill Washington 25, D. C.	1
N 123	Chief, Bureau of Ships Department of the Navy Washington 25, D. C. Attn: Code 817	1
U 56	Massachusetts Institute of Technology Lincoln Laboratory P. O. Box 73 Lexington 73, Mass. Attn: Dr. Benjamin Lax Group 35, Room C-318	1
U 275	Massachusetts Institute of Technology Lincoln Laboratory P. O. Box 73 Lexington 73, Mass. Attn: R. Rediker	1
U 313	Massachusetts Institute of Technology Cambridge 39, Mass. Attn: Prof. D. White	1
U 373	Kansas State University Manhattan, Kansas Attn: Dr. Brock Dale	1
U 436	University of Mississippi University, Mississippi Attn: Mr. Thomas Tullos	1
	AFCRL, Office of Aerospace Research (CRVPD, Mr. R. F. Cornelissen) L. G. Hanscom Field Bedford, Mass.	5 + remaining

<p>AF Cambridge Research Laboratories, Bedford, Mass. Electronics Research Directorate</p> <p>SEMICONDUCTOR DEVICE CONCEPTS, by N. Holonyak, Jr., February 28, 1963, 15pp. AFCLR-63-120(B) Unclassified report</p> <p>A status report on the preparation and properties of Ga(As<sub>1-x</sub>P<sub>x</sub>) p-n junction lasers is presented. Halogen vapor transport synthesis of Ga(As<sub>1-x</sub>P<sub>x</sub>) and its preparation into laser junctions are described. Electrical and optical properties of Ga(As<sub>1-x</sub>P<sub>x</sub>) laser junctions are discussed. The present limitations in these prop- erties are related to material prob- lems and the very early state of devel- opment of Ga(As<sub>1-x</sub>P<sub>x</sub>), and are dis- cussed in this context.</p>	<p>UNCLASSIFIED</p> <p>1. Introduction</p> <p>2. Prep. Ga(As<sub>1-x</sub>P<sub>x</sub>) Crystals and Laser p-n Junctions</p> <p>3. Elec. and Opti- cal Prop. of Ga(As<sub>1-x</sub>P<sub>x</sub>) Las- er Junctions</p> <p>I. Holonyak, N. Jr.</p>	<p>UNCLASSIFIED</p> <p>1. Introduction</p> <p>2. Prep. Ga(As<sub>1-x</sub>P<sub>x</sub>) Crystals and Laser p-n Junctions</p> <p>3. Elec. and Opti- cal Prop. of Ga(As<sub>1-x</sub>P<sub>x</sub>) Las- er Junctions</p> <p>I. Holonyak, N. Jr.</p>
<p>AF Cambridge Research Laboratories, Bedford, Mass. Electronics Research Directorate</p> <p>SEMICONDUCTOR DEVICE CONCEPTS, by N. Holonyak, Jr., February 28, 1963, 15pp AFCLR-63-120(B) Unclassified report</p> <p>A status report on the preparation and properties of Ga(As<sub>1-x</sub>P<sub>x</sub>) p-n junction lasers is presented. Halogen vapor transport synthesis of Ga(As<sub>1-x</sub>P<sub>x</sub>) and its preparation into laser junctions are described. Electrical and optical properties of Ga(As<sub>1-x</sub>P<sub>x</sub>) laser junctions are discussed. The present limitations in these prop- erties are related to material prob- lems and the very early state of devel- opment of Ga(As<sub>1-x</sub>P<sub>x</sub>), and are dis- cussed in this context.</p>	<p>UNCLASSIFIED</p> <p>1. Introduction</p> <p>2. Prep. Ga(As<sub>1-x</sub>P<sub>x</sub>) Crystals and Laser p-n Junctions</p> <p>3. Elec. and Op- tical Prop. of Ga(As<sub>1-x</sub>P<sub>x</sub>) La- ser Junctions</p> <p>I. Holonyak, N. Jr.</p>	<p>UNCLASSIFIED</p> <p>1. Introduction</p> <p>2. Prep. Ga(As<sub>1-x</sub>P<sub>x</sub>) Crystals and Laser p-n Junctions</p> <p>3. Elec. and Opti- cal Prop. of Ga(As<sub>1-x</sub>P<sub>x</sub>) Las- er Junctions</p> <p>I. Holonyak, N. Jr.</p>